



THE LEADING DESIGNER &
Manufacturer of
Narrow Fabrics

For further information about ACW Webbing, please contact us at **(401) 762-5500** or visit **www.acw1.com**

FIBER COMPARISON CHART

PROPERTY	NYLON	POLY-PRO	COTTON	POLYESTER	KEVLAR
COST	3	1	5	4	8
STRENGTH	8	5	2	7	9
ABRASION RESISTANCE	8	6	2	10	7
RESISTANCE TO UV	Good	Good	Fair	Excellent	Fair
MILDEW RESISTANCE	Fair	Excellent	Poor	Excellent	—
RESISTANCE TO ACIDS	Poor	Excellent	Poor	Good	Good
RESISTANCE TO ALKALIS	Good	Excellent	Poor	Good	Good
RESISTANCE TO OIL AND GAS	Good	Excellent	Poor	Good	Excellent
MELTING POINT	420 F	330 F	CHARS AT 300 F	480 F	DECOM 900 F
CUT RESISTANCE	5	5	5	5	10

● 1 = LOW | 10 = HIGH

For more information about ACW Specialty Webbing products, please contact ACW, Inc. at **401-762-5500** or visit us on the web at **www.acw1.com**

